

Nanovia PC V0 :

Inflammable UL94 VO

La température de transition vitreuse de 140 °C permet l'impression de pièces résistantes à la chaleur.

Le Nanovia PC-V0 est idéal pour la réalisation d'outillages composites pour l'infusion, le pré-imprégné ou encore le drapage AFP.



Avantages:

Bonne résistance au feu et la chaleur • Résistant aux chocs • Propriétés mécaniques

Impression 3D		Mécaniques	Thermiques	
T° Extrusion	250 - 270 °C	Densité	1,13 g/cm3 (ASTM D792)	MFI
T° Plateau	100 - 140 °C	Mod. traction	700 MPa (ASTM D638)	10 g/10min (300°C, 1.2 kg / D1238)
T° Enceinte	> 100 °C	Mod. flexion	2000 MPa (ASTM D790)	144 °C (D648 @ 4.6 kg/cm2)
Buse	Tous	Elong. à la rupture	120 % (ASTM D638)	50 °C (D648 @ 18.6 kg/cm2)
Retrait	0,5 to 0,7 %	IZOD (entaillé)	65 kJ/m² (ASTM D256)	5.5 x 10^-5 mm/mm/°C (D696)
Abs. Humidité	0,15 % (D570)	Electriques		V-0 UL 94 at 3.0 mm
Masse linéique	3,05 g/m (1.75 mm) 8,10 g/m (2.85mm)	Vol. resistivité	4x10^16 Ω.cm (D257)	300 °C
Couleurs	Translucide, blanc, noir	Force diélectrique	30 kV/mm (D149)	120 °C
		Const. diélectrique	2,80 D150	
		Fact. dissipation	0,0082 D150	
		ARC resistance	120 Sec	

Conseils d'utilisation

Stockage

- Il est conseillé de stocker vos bobines dans un endroit sec à l'abri de la lumière, si possible accompagnées de dessiccant.
- Pour assurer une parfaite impression il est conseillé d'étuver votre filament à 100 °C pendant 4h ou plus, lorsque la bobine a été exposée à l'air libre pendant une longue période.

Post traitement

- Pour une utilisation en extérieur, nous vous conseillons de peindre vos pièces ou de les soumettre à un traitement anti UV, le PC étant sensible aux UV et risque de jaunir.

Hygiène & sécurité

Impression

- Il est conseillé d'imprimer ce matériau dans une zone équipée d'une extraction d'air ou d'une protection adaptée.

Post traitement

- Le port d'EPI standard (masque, gants) est conseillé lors du post traitement des pièces imprimées avec le Nanovia PC-V0.



Nanovia PC V0 :

Non-flammable UL94 VO

With a glass transition temperature of 140°C and certified fire resistant UL 94 V0, Nanovia PC-V0 allows for both mechanical and fire resistant 3D prints. Ideal for the creation of molds for composite infusion, pre impregnated or even AFP draping.



Avantages:

Great fire and heat resistance • Shock resistant • Good mechanical properties

3D Printing

Extrusion T°	250 - 270 °C
Plate T°	100 - 140 °C
Enclosure T°	> 100 °C
Nozzle	All
Warping	0.5 to 0.7 %
Humidity abs.	0.15 % (D570)
Linear weight	3.05 g/m (1.75 mm) 8.10 g/m (2.85mm)
Colours	Translucid, white, black

Mechanical

Density	1.13 g/cm3 (ASTM D792)
Tensile mod.	700 MPa (ASTM D638)
Flexural mod.	2000 MPa (ASTM D790)
Elong. at break	120 % (ASTM D638)
IZOD (notched)	65 kJ/m ² (ASTM D256)

Electric	
Resistivity vol.	4×10 ⁻¹⁶ Ω.cm (D257)
Dielectric str.	30 kV/mm (D149)
Dielectric con.	2.80 D150
Dissipation fact.	0.0082 D150
ARC resistance	120 Sec

Thermal

MFI	10 g/10min (300°C, 1.2 kg / D1238)
HDT	144 °C (D648 @ 4.6 kg/cm ²)
Thermal expansion	50 °C (D648 @ 18.6 kg/cm ²)
Flammability	5.5 × 10 ⁻⁵ mm/mm/°C (D696)
Fusion T°	V-0 UL 94 at 3.0 mm
Tg	300 °C
	120 °C

Application

Storage

- Store Nanovia PC-V0 in a dry and dark location, if possible with a desiccant.
- In order to guarantee good printing conditions dehydrate Nanovia PC-V0 at 100 °C for 4 hours or longer, when the spools has been exposed to moisture for an extended period.

Post treatment

- For an outdoor usage, it's recommended either paint or apply a protective UV coating, to prevent the polycarbonate from hydrolyzing and yellowing.

Health and safety

Printing

- We recommend printing Nanovia PC-V0 in a room equipped with air extraction or by using appropriate breathing equipment.

Post treatment

- We recommend wearing standard safety equipment during the post treatment of your prints made with Nanovia PC-V0.



SMART MATERIALS for
ADVANCED INDUSTRIALS